

PERESEAL AF BATHROOM & KITCHEN SILICONE SEALANT

Technical Data Sheet

Page 1 of 2

Technical Data

Curing system	Neutral (oxime)
Appearance	Non-sagging paste
Odour	Low oxime smell
Specific gravity	1.01 ± 0.03
Shore A hardness	Approx. 30
Elongation	400%
Tensile strength	Approx. 1.20 MPa
Tack-free time	Within 15 minutes
Application temperature	-20°C to +50°C
Service temperature	-50°C to +150°C
Shelf life	12 months

Product

PERESEAL® AF is a single-component, 100% RTV neutral silicone sealant with anti-fungal properties. It resists mould and mildew in areas exposed to high humidity and temperature and forms a durable, flexible, waterproof seal on most building materials.

Features

- Mould and mildew resistant (contains fungicide)
- Neutral oxime curing system
- Non-corrosive to metals, alkaline substrates and automobiles
- Outstanding durability
- One part; no mixing
- Permanently flexible
- Excellent gunnability from -20°C to +50°C
- Waterproof and weatherproof
- Low shrinkage
- Non-sagging
- Primerless adhesion to most materials

Uses

- General glazing of masonry, concrete, ceramic, stone, glass, metals, stainless steel, aluminium, most plastics, wood, brick, zinc and galvanised iron
- Sealing of kitchen and bathroom fittings, sanitary areas, cold storage, clean rooms, containers, automobiles, rainwater goods, roofing and building/civil-engineering joints
- DIY applications including gutters, air-conditioning, sanitary work, cars, boats and marine uses

Preliminary compatibility tests are recommended before application.

The information in this document is based on current product data and is provided in good faith. Because materials, substrates and applications vary beyond our control, users should carry out preliminary compatibility tests. No warranty is expressed or implied.

Technical Data Sheet
PERESEAL AF BATHROOM & KITCHEN SILICONE SEALANT
 Revision No. 2
 Issued: 16 September 2026

PFE Technologies Pte Ltd
 9 Gul Street 4, Singapore 629238
 Tel: +65 6558 6388 | Fax: +65 6558 7310
 Email: sales@pfetech.com | Website: www.pfetech.com

PERESEAL AF BATHROOM & KITCHEN SILICONE SEALANT

Technical Data Sheet

Page 2 of 2

Not recommended for

- Not recommended for aquariums.
- Not for traffic areas or areas subject to abrasion.
- Not for paint coatings.
- Not for polycarbonate or polyacrylate under tension.
- Not for copper materials.

Curing time

Tack-free in approximately 15 minutes and cures to a depth of 10 mm in 7 days. Dry or low-humidity conditions may require longer.

Storage

Store in a dry, cool place between +5°C and +30°C. Shelf life is 12 months in unopened packaging.

Caution

Read and understand the Safety Data Sheet before handling or use.

Joint design

Size the sealant bead for anticipated joint movement. Maximum $\pm 30\%$ compression and extension capability. Minimum bead size: 3 mm $\times$ 3 mm. Maximum joint size: 30 mm. Typical depth $\times$ width combinations: 6 mm $\times$ 6 mm, 8 mm $\times$ 12 mm and 10 mm $\times$ 20 mm.

Application

- Ensure surfaces are clean and dry.
- Mask smooth surfaces where needed for easier clean-up.
- Use an approved backing material in the joint where required.
- Cut the nozzle to the desired size.
- Insert the cartridge into the caulking gun.
- Push the sealant ahead of the nozzle to form a uniform bead.
- Tool within 5 minutes.
- Remove excess uncured sealant with MEK or toluene, observing the solvent manufacturer's safety instructions.

Technical note

Technical values shown are typical values for the current formulation and are provided in good faith. They are not intended for use as product specifications.

The information in this document is based on current product data and is provided in good faith. Because materials, substrates and applications vary beyond our control, users should carry out preliminary compatibility tests. No warranty is expressed or implied.